



Confidential Report

Our Ref: 27/04019/09/16



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 5 October 2016
Our Ref: 27/04019/09/16
Your Ref:
Page: 1 of 3

Client: Mermet SAS
58 Chemin du Mont Maurin
38630 Veyrins – Thuelin
France

Job Title: Fire Test on One Sample of Fabric

Client's Order No: --

Date of Receipt: 27 September 2016

Description of Sample(s): One sample of fabric reference Karellis 11301

Work Requested: We were asked to make the following test(s):
BS 5867:Part 2:Type B

* subcontracted test, UKAS accredited
** subcontracted test, EN ISO/IEC 17025 accredited
*** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 5 October 2016

Our Ref: 27/04019/0916

Your Ref:

Page: 2 of 3

Client: Mermet SAS

Fire Tests According to BS 5867-2:Type B:2008 Fabrics for curtains, drapes and window blinds – Flammability requirements, Specification

Date of Test: 05/10/16

Procedure

The specimen were tested in accordance with BS EN ISO 15025:Procedure A:2002, as required by BS 5867:Type B.

Sets of specimens were tested before and after the water soaking procedure described in BS EN 1021-1:Annexe D:2006.

The specimens were tested using a flame application time of 15 seconds.

Requirements

BS 5867 states that:-

‘No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of the sample. If any part of any hole or any part of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements for type ‘B’ of this British Standard.’



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2016 Shirley Technologies Limited. All rights reserved.



Date: 5 October 2016
Our Ref: 27/04019/09/16
Your Ref:
Page: 3 of 3

Client: Mermet SAS

Results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Before Water Soaking

Number of specimens where the hole reached any edge – 0
Number of specimens where the flame reached any edge – 0
Number of specimens where there was flaming debris droplets – 0

After Water Soaking


Number of specimens where the hole reached any edge – 0
Number of specimens where the flame reached any edge – 0
Number of specimens where there was flaming debris droplets – 0

Comments

The results indicate the sample meets the Type B performance requirements.

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by:.....  R Ryan, Fire Technician

Countersigned by:.....  P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.



1066